



Facet-dependent Rock-salt Reconstruction on the Surface of Layered Oxide Cathodes

Hanlei Zhang^{1,2}, Brian M. May^{2,3}, Jon Serrano-Sevillano⁴, Montse Casas-Cabanas⁴, Jordi Cabana^{2,3},
Chongmin Wang^{5*}, Guangwen Zhou^{1,2*}

1. Materials Science and Engineering Program & Department of Mechanical Engineering, State University of New York, Binghamton, New York 13902, United States
2. NorthEast Center for Chemical Energy Storage, State University of New York, Binghamton, New York 13902, United States
3. Department of Chemistry, University of Illinois at Chicago, Chicago, Illinois 60607, United States
4. CIC Energigune, Albert Einstein 48, Parque Tecnológico de Álava, Miñano 01510, Spain
5. Environmental Molecular Sciences Laboratory, Pacific Northwest National Laboratory, Richland, Washington 99352, United States

Chem. Mater., Just Accepted Manuscript

DOI: 10.1021/acs.chemmater.7b03901

Publication Date (Web): January 2, 2018

Copyright © 2018 American Chemical Society

Abstract

The surface configuration of pristine layered oxide cathode particles for Li-ion batteries significantly affects the electrochemical behavior, which is generally considered to be a thin rock-salt layer in the surface. Unfortunately, aside from its thin nature and spatial location on the surface, the true structural nature of this surface rock-salt layer remains largely unknown, creating the need to understand its configuration and the underlying mechanisms of formation. Using scanning transmission electron microscopy, we have found a correlation between the surface rock-salt formation and the crystal facets on pristine $\text{LiNi}_{0.80}\text{Co}_{0.15}\text{Al}_{0.05}\text{O}_2$ primary particles. It is found that the originally $(014\bar{1})$ and (003) surfaces of the layered phase result in two kinds of rock-salt reconstructions: the (002) and (111) rock-salt surfaces, respectively. Stepped surface configurations are generated for both reconstructions. The (002) configuration is relatively flat with monoatomic steps while the (111) configuration shows significant surface roughening. Both reconstructions reduce the ionic and electronic conductivity of the cathode, leading to a reduced electrochemical performance.